

Product Description

Glass fiber reinforced Urethane/Vinyl ester hybrid BMC suitable for encapsulation of pultruded composites.

General

Material Status	• Commercial: Active		
Availability	• North America • Asia Pacific	• Europe • South America	
Filler / Reinforcement	• Glass Fiber and Mineral Filler		
Features	• Good adhesion to pultrusion • Cure and release from rotating die	• Good chemical resistance • Outstanding flow	• Pigmentable
Processing Method	• This BMC product is generally intended to be compression/injection molded in matched metal molds, typically at 300°F (150°C) and 500 to 1,000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process. Available in bulk or extrusions.		
Resin	• Urethane/Vinyl ester Hybrid		

Physical	Typical	Unit	Test Method
Density	1.53	g/cm ³	ASTM D792
Mold Shrinkage (RT mold/RT part)	0.00322	in/in	ASTM D955
Water Absorption, 24 hrs., 23°C	0.095	%	ASTM D570
Poisson's Ratio	0.36		ASTM D638
Mechanical (As molded)	Typical	Unit	Test Method
Tensile Modulus	2.4 E+6 (14)	psi (GPa)	ASTM D638
Tensile Strength	4,500 (31)	psi (MPa)	ASTM D638
Flexural Modulus (RT)	1.4 E+6 (9.7)	psi (GPa)	ASTM D790
Flexural Strength	14,000 (95)	psi (MPa)	ASTM D790
Impact	Typical	Unit	Test Method
Izod Notched Impact Strength	6.9 (370)	ft-lb/in (J/m)	ASTM D256
Unnotched Impact Strength	9 (480)	ft-lb/in (J/m)	ASTM 4812

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2019

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.